

Product Datasheet



BU Powder Coatings
Interpon100 GLOSS White- BA003G

AkzoNobel
Tomorrow's Answers Today

Product Description

BA003G is a highly chemically resistant powder coating formulated for use as a lining for metal drums used for the bulk transportation of general industrial chemicals. It is fully FDA compliant. **BA003G** does not comply with EU statement 1895/2005 and so should not be used for food contact applications within the European Union.

Long term exposure to ultraviolet light or exterior weathering is not recommended

Powder Properties

Chemical type	Epoxy
Particle Size	Suitable for electrostatic spray
Specific gravity	1.5-1.6 g/cm ³
Storage	Dry cool conditions below 25°C
Shelf life	12 months
Sales Code	BA003G
Stoving schedule (object temperature)	10 - 20 minutes at 200°C 6 - 12 minutes at 230°C

Test Conditions

The results shown below are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

Substrate	Mechanical tests: Gold Seal polished steel Chemical & durability tests: Gold Seal lightweight
Pretreatment	Zinc Phosphate
Film Thickness	50 microns

Mechanical Tests

Flexibility	ISO6860 (Conical Mandrel)	Pass 3mm
Adhesion	BS EN ISO 2409 (2mm Crosshatch)	Gt 0
Erichsen Cupping	ISO1520	Pass >7mm
Hardness	BS EN ISO 1518 (2000gms)	Pass - no penetration to substrate
Impact	BS3900-E3	Pass 2mm

Chemical and Durability Tests

Salt Spray	ISO7253 (250 hours)	Pass - no corrosion creep more than 2mm from scribe
Cyclic Humidity	BS3900-F2 (1000 hours)	Pass - no blistering or loss of gloss
Distilled Water Immersion	BS3900-F7 (240 hours)	Pass - no blistering or loss of gloss
Exterior Durability	Some chalking and loss of gloss after 3-6 months continuous outdoor exposure. Protective properties retained	
Colour Stability at elevated temperatures	Fair - gradual yellowing of white and pastel shades on continuous exposure above 100°C	
Chemical Resistance	BA003G has been formulated to have resistance to a wide range of general industrial regarding specific chemicals and/or foodstuffs resistance contact Akzo Nobel chemicals and foodstuffs. For more regarding specific chemicals and/or foodstuffs resistance contact Akzo Nobel	

Pretreatment	Aluminium, steel or Zintec surfaces to be coated must be clean and free from grease. Iron phosphate and particularly lightweight zinc phosphating of ferrous metals improves corrosion resistance. Aluminium substrates may require a chromate conversion coating.
Application	Interpon100 powders can be applied by manual or automatic electrostatic spray equipment. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.
Additional Information	Interpon100HR (High Reactivity) powders are also available for use where a lower stoving temperature or shorter curing schedule is required. Sales code: B-Series Stoving schedule: 30 minutes at 130°C (object temperature) 15 minutes at 150°C 5 minutes at 180°C Shelf life: 6 months For further details on powder properties and film performance of Interpon100HR please contact AkzoNobel.
Safety Precautions	Please consult the Material Safety Datasheet (MSDS)

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advice given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel